

THE TECHNICAL DATA SHEET

ELLAS K-792A

Physical Properties

Item	ASTM Method	Unit	Result/Remark
Specific Gravity	D 792		1.21
Hardness	D 2240	Shore A	92
100% Tensile Stress	D 412	Kgf/cm ²	100
Tensile Strenght	D 412	Kgf/cm	500
Elogation	D 412	%	500
Tear Strenght	D 624	Kgf/cm	124

*These are typical values and should not be used for establishing specifications.

Applications: Injection Molding for Transparent parts
Extrusion Molding for Film/Sheet, Tube/Hose

Injection Molding Temperature (°C)

C1	C2	C3	Nozzle
175 – 190	180 – 195	190 – 205	190 – 200

Extrusion Molding Temperature (°C)

C1	C2	C3	C4	Head	Die
160 – 175	175 – 190	175 – 190	185 – 200	185 – 200	180 – 195

* These recommended processing conditions can be varied on your machine design conditions.

* Please dry and use TPU before processing it.

* If you have any trouble in processing it, contact us.

API-  KOLON
Engineering Plastics

333 Enterprise Parkway · Lake Zurich · IL · 60047 · USA

Telephone: 847-550-5556 Fax: 847550-5557

E-mail: MaxHahn21@hotmail.com